

TECHNICAL DATA SHEET

Cut Edge Corrosion System

Reference	SWT Corrosion Primer	Flexlap
Purpose/Uses	<i>Rust and wet tolerant for use with Liquasil polymers</i>	<i>Cut Edge Corrosion Treatment</i>
Colour	<i>Grey</i>	<i>Goosewing Grey plus RAL Colour Range</i>
Application	<i>Brush or Roller</i>	<i>Apply by Brush - Roller</i>
Volume Solids	<i>100%</i>	<i>100%</i>
Recommended Film Thickness	<i>@100um Heavily rusted or pitted surfaces may require 2 coats</i>	<i>350-500 microns</i>
Coverage Rate	<i>Approx 40 linear metres per 1.0 kg tin</i>	<i>Approx 40 linear metres @ 150mm band thickness per litre</i>
Drying Time	<i>Allow 6-24 hours drying time</i>	<i>Rain free - 2 to 3 hours Thoroughly dry- 16 hours</i>
Thinners/Brush wash	<i>Use Sacrificial Brushes</i>	<i>Xylene</i>
Weight per Litre	<i>1.0 kg</i>	<i>0.98 at 20° C</i>
Flash Point	<i>> 100° C</i>	<i>Above 32° C</i>
V.O.C.	<i>V.O.C. Free</i>	<i>V.O.C. Free</i>
Finish	<i>Semi Gloss</i>	<i>Semi Gloss</i>
Application Temperature	<i>-20° C +40° C Note: Tins must be kept cool and out of direct sunlight during summer months to avoid premature curing</i>	<i>-5° C +60° C</i>
Approvals	<i>ABS Certified, IMO Approval, Lloyds Approval Ballast Tank Maintenance Coating Lloyds Type Approval: New Build Applications (Bore Steel and Shop Primers)</i>	<i>BBA Certification 18/5536</i>
Surface Preparation	<i>Remove existing or factory finishes and prepare to bare metal</i>	<i>All surfaces must be clean and thoroughly dry, particularly at joints</i>

FOR PROFESSIONAL USE ONLY

June 2018 - Version 3.0 Liquasil Limited - all rights reserved

Liquasil Limited

Unit 3 Radway Industrial Estate, Radway Road, Solihull, West Midlands B90 4NR

t 0121 709 5352 e info@liquasil.com w www.liquasil.com



 LIQUASIL

Cut Edge Corrosion System

LIQUID ROOFING SOLUTIONS

Application Method

Cut Edge Corrosion System

Liquasil does not normally recommend the sealing of overlapping roof sheets, nor treatment to the bottom roof sheets where no corrosion exists.

- Remove existing finishes and prepare to bare metal in a straight line, including profile crowns. Feather-in edges of existing / factory finishes. Surface rust may remain.
- Apply a single coat of Liquasil SWT Corrosion Primer to the prepared area at a film thickness of 100 microns
- Allow SWT Corrosion Primer to cure before applying a single coat of Liquasil Flexlap polymer finish at a wet film thickness of 350 – 500 microns. Surfaces must be bone-dry during application.



Preparation



Primer Applied



Completed Installation

Corrosion Primer – Important Notes

- The SWT Primer is a two-part epoxy comprising the primer (part A) and the hardener (part B)
- Part B is corrosive. Operatives must wear suitable PPE when handling
- Carefully and thoroughly stir one bottle of activator (Part B) into the tin of primer (Part A)
- Use the contents immediately. The contents will cure in the can in approximately 20-50 minutes depending on ambient temperature. Do not leave unopened cans unattended.
- On sunny days, keep the contents of the SWT Primer (both parts) in the shade and at a temperature below 20°C (store in a bucket of water on hot days). This measure helps prevent exothermic build-up during the products' chemical reaction, which can occur and causes the mixed contents to become very hot.

The primer can be installed on wet or damp surfaces, but will need more working with the brush. For ease of application, loosely towel dry the area to be treated to remove excess water.

Drying time is approx. 4 hours at 15°C and up to 24 hours curing time.

Over-coating time is unlimited.

Please refer to relevant MSDS sheets for further information.

The above instructions assume that no rust / rot is present to the bottom roof sheets where overlaps occur.

Non-Standard Installations

If an existing cut edge corrosion system is present, refer to Liquasil for further instructions or site survey.

Note that severely corroded roofs may not qualify for the Liquasil Latent Defects insurance Guarantee.

